

UTILISATION OF SUGARMILL WASTE IN MANUFACTURING OF BRICKS

M. Rajiv¹, M.Arun Pandiyan², G.Sofia³, M.Abinaya⁴

1 Assistant professor / Department of Civil Engineering, Saranathan College of Engineering,
Panjappur, Trichy Dt-620012

2, 3 Assistant professor / Department of Civil Engineering, Kings College of Engineering,
Punalkulam, Gandarvakottai post, Pudukkottai Dt-613303

4, UG Civil Engineering Students, Kings College of Engineering, Punalkulam,
Gandarvakottai post, Pudukkottai Dt-613303

Abstract—In India, bricks are usually made up of clay, and are generally produced in traditional, unorganized small scale industries. Brick making consumes larger amount of clay which leads to top soil removal and land degradation. To avoid all this environmental threats an attempt was made to study the behavior of bricks manufactured using, waste materials from sugarcane industrial waste. Recycling of such waste as raw material alternatives may contribute in the exhaustion of the natural resources and reduction in waste disposal costs. In this project we choose sugarcane bagasse ash (SBA) and press mud in ordinary Portland cement (OPC) stabilized bricks. The brick was manufactured of size 25cm x 12cm x 6.5cm. The blocks were named as 4, 6 and 8 then it is added with SBA and press mud by weight of dry soil, then the bricks followed by curing for period of 28 days. The test like compressive strength, water absorption test, shape and size test in accordance with Bureau of Indian standards (BIS) specifications by also considering the cost.

Key words: *sugarcane bagasse ash (SBA), press mud, ordinary Portland cement, cost effective.*

I. INTRODUCTION:

There is a strong demand for environmentally safe reuse and effective disposal method for bagasse ash and press mud due to the increasing amount of sludge generated by the various industries or plant in India. Landfills are commonly used for disposal of sludge in India; rapid urbanization has made it increasingly difficult to find suitable landfill sites. Therefore, incineration has become one of the few alternatives available for disposal of sludge. The ultimate disposal of incinerated bagasse ash and

press mud can be accomplished by using it an engineering construction material. One possible solution for the management of this sludge is to reuse it as a building material, namely, to incorporate this bagasse ash and press mud into bricks. The fired clay brick is one of the most common and abundant masonry building materials and remain popular for its many characteristic properties. As such, the recycling of waste materials by incorporating them into bricks has been a popular topic of investigation over the last century, with varying degrees of success across a wide range of waste material. This popularity is likely due to flexibility on the type of wastes which can be mixed into the brick making material, but more importantly, the high temperature involved in firing the bricks allows for the volatilization of dangerous Component, as well as the fixation of wastes into the vitreous phase of the brick. The current study investigates the potential for reusing sugarcane sludge or bagasse ash and press mud by using it as a partial replacement material.

II.SCOPE:

- To promote the solid waste from the sugar mills as a useful product
- To manage the disposal of waste product into construction raw material
- To dispose the waste safely
- To encourage the waste products as eco friendly material
- To make the bricks which are energy efficient which is the only viable solution to

the environmental concerns and natural resources conservation for future generations

III. LITERATURE REVIEW

As we all know that the waste from the industries is very harmful for the environment as well as to our health, if not disposed in proper manner. The fibrous residue of sugarcane after crushing and extraction of its juice, known as “bagasse” is one of the largest agriculture residues in the world. The bagasse is however used as a biomass fuel for boilers, but after burning the by-product left is of no use and generally disposed into the rivers which affect the health of human being, environment, fertile land, sources of water bodies etc. Depending on the incinerating conditions, the resulting sugarcane bagasse ash (SCBA) may contain high levels of SiO₂ and Al₂O₃. Uses of Sugarcane bagasse ash waste in brick can save the sugarcane industry disposal costs and produce a ‘greener’ bricks for construction.

Indian sugarcane crop cultivation forms an important part of the Indian agricultural economy. Production of sugar has shown a phenomenal increase in the last 65 years. One of the byproducts of sugar industry is pressmud, a solid residue, obtained from sugarcane juice before crystallization of sugar. Generally pressmud is used as manure in India. The aim of the present investigation is to recover protein, sugar and wax from pressmud. The amount of protein is estimated to be 3.3%. The percentage of sugar is about 0.8%. Extraction of Wax by solvent has resulted in a recovery of about 12%.

IV. MATERIALS:

A. Sugarcane Bagasse Ash:



Fig 1. Sugarcane bagasse ash

The burning of bagasse which a waste of sugarcane produces bagasse ash. Presently in sugar factories bagasse is burnt as a fuel so as to run their boilers. India alone generates 90 million t of bagasse as a waste material, from sugarcane industry. Bagasse is a residue obtained from the burning of bagasse in sugar producing factory. Bagasse is the cellular fibrous waste product after the extraction of the sugar juice from cane mills. Its currently used as a bio-fuel and in the manufacture of pulp and paper products and building materials. For each 10 tons of sugarcane crushed, a sugar factory produces nearly 3.1 tons of wet bagasse which is a by-product of the sugarcane industry. When this bagasse is burnt the resultant ash is bagasse ash. Western Maharashtra is having maximum number of sugar factories, these factories faces a disposal problem of large quantity bagasse. The effective use of these waste products is a challenging task for a researcher through economical and environmental impact.

Properties:

- Physical properties of cement and bagasse ash:

Material	Density (Kg/cu.m)	Specific gravity	Fineness passing 45µm	Specific surface area (cum/Kg)	Mean grain size (µm)
Cement	1.15	3	82	300	2.1
Bagasse ash	0.4	1.8	95	900	5.1

Tab1. Physical properties of cement and bagasse ash

- Chemical properties of bagasse ash:

Sl.NO	Component	Mass %
1	Silica (SiO ₂)	66.89
2	Alumina (AL ₂ O ₃) Ferric oxide (Fe ₂ O ₃)	29.18
3	Calcium oxide (CaO)	1.92
4	Magnesium oxide (MgO)	0.83
5	Sulphur tri oxide (SO ₃)	0.56
6	Loss of Ignition	0.72
7	Chloride	-

Tab2.chemical properties

B. Press Mud:

Pressmud from the sugar mills is a very useful source of fertilizer as well as some chemicals. The major use that has recently been developed in India is in biocomposting (usually trade named as Bioearth) where it is treated with the spent wash from the distillery. The concept of biological degradation of organic wastes by anaerobic digestion for the generation of methane has been used by waste management industries for many years. Pressmud is an industrial waste available from the sugar mills.



Fig2.Press mud

The above waste materials are used as a replacement for cement and fine aggregate. Other than waste materials the materials which used in the manufacturing of bricks are as follows:

C. Ordinary Portland Cement:

Portland cement is the most common type of cement in general use around the world, used as a basic ingredient of concrete, mortar, stucco, and most non-speciality grout.

The magnesium oxide content (MgO) shall not exceed 5.0% by mass. Cement sets when mixed with water by way of a complex series of chemical reactions still only partly understood. The different constituents slowly crystallise and the interlocking of their crystals gives cement its strength. Carbon dioxide is slowly absorbed to convert the portlandite (Ca(OH)₂) into insoluble calcium carbonate. After the initial setting, immersion in warm water will speed up setting. Gypsum is added as an inhibitor to prevent flash setting and quick setting.

Properties:

Physical Properties:

Compressive strength (MPA)	44
Fineness (%)	8
Specific gravity	3.157
Initial setting time (Minute)	65
Final setting time	320

Tab3.physical properties of cement



Fig.3 ordinary Portland cement

D. Fine Aggregate:

Fine aggregate was purchased which satisfied the requirement of fine aggregate required for experimental work and conforming to zone-2, as per IS 383:1970. The sand was oven-dried and sieved to

Sl.no	Name of the brick (for identification)	Amount of cement Added (kg)	Amount Of fine Aggregate (kg)	Amount of Bagasse Ash (kg)	Amount of press Mud (kg)
1	4	1 1/2	1 1/2	1/2	1/2
2	6	1	1	1	1
3	8	1/2	1/2	1 1/2	1 1/2

eliminate any foreign particles before mixing. Locally available natural sand with 4.75 mm maximum size was used as fine aggregate, having specific gravity, fineness modulus and unit weight as given

- 1) Fineness modulus=2.81
- 2) Specific gravity=2.61
- 3) Silt content=2.63



Fig4.fine aggregate

E. Water:

Water is an important ingredient of brick as it actually used for manufacturing of brick. Since it helps to bind all the raw materials for giving proper

mix. Water used for making brick should be free from impurities. The common specifications regarding quality of mixing water is water should be fit for drinking. Such water should have inorganic solid less than 1000 ppm. This content lead to a solid quantity 0.05% of mass of cement when w/c ratio is provided 0.5 resulting small effect on strength.

IV.MIX DESIGN

Tab4.Mix design

V.METHODOLOGY:

A. Drying Of Waste Materials:



Fig5.Sugar cane bagasse ash



Fig6.Drying of press mud

The waste materials are sun dried for a period of 12 hours to eliminate the water content.

B. Sieve Process:



It is essential to sieve the fine aggregate and bagasse ash in Is sieve size of 4.5mm for the proper binding of bricks.

C. Mixing of materials:



Fig8.Mixing

The above materials are mixed based on the mixed design for proper binding.

D. Casting of bricks:



Fig9.casting

The mixture is casted in the mould of size 250mmx120mmx65mm.

E. Casted bricks:



Fig10.Casted bricks

The casted bricks are named as 4,6,8 based on the mix design, then the bricks are sun dried for a period of 5hrs and it is subjected to curing for 28 days . The cured bricks are undergone various test for identifying the strength.

VI.TEST ON BRICKS:

A. Compressive Strength Test / Crushing Strength:

The brick specimens are immersed in water for 24 hours. The specimen is placed in compression testing machine with 6 mm plywood on top and bottom of it to get uniform load on the specimen. Then load is applied axially at a uniform rate of 10 N/mm². The crushing load is noted for the bricks named 4, 6, and 8.

B. Water Absorption Test:

A brick is taken and it is weighted dry. It is then immersed in water for a period of 16 hours. It is weighed again and the difference in weight indicates the amount absorbed by the brick. It should not in exceed 20 percent of weight of dry brick.

C. Shape And Size Test:

In this test, a brick is closely inspected. It should be of standard size and its shape should be truly rectangular with sharp edges. For this purpose 3 bricks are selected at random and they are stacked length wise ,along the width and along the height.

VII.CONCLUSION:

Based on the above experimental procedure and test, we conclude as;

1. Use of bagasse ash and pressmud in brick can solve the disposal problem; reduce cost and produce a 'greener' Eco- friendly bricks for construction.
2. The crushing strength or compressive strength of bricks named as 4 is 12N/mm² and the brick named as 6 is 6N/mm² and the brick named as 8 is 5N/mm².
3. Hence we strongly recommend brick 4 has a good compressive strength and suitable for construction.
4. Environmental effects of wastes and disposal problems of waste can be reduced through this brick manufacturing process.
5. This study helps in converting the non-valuable bagasse ash and press mud into bricks and makes it valuable.
6. In this research maximum compressive strength can be attained.
7. The expected cost of the bricks can be reduced.

References

1. A. P. Singh and P. Kumar, "Light weight cement-sand and bagasse ash bricks," *International Journal of Innovative Research in Science and Technology*, vol. 1, no. 12, pp. 284–287, 2015. M. V. Madurwar, S. A. Mandavgane, and R. V. Ralegaonkar
2. "Use of sugarcane bagasse ash as brick material," *Current Science*, vol. 107, no. 6, pp. 1044–1051, 2014.
- [27] A. Kulkarni, S. Raje, and M. Rajgor, "Bagasse ash as an effective replacement in flyash bricks," *International Journal of Engineering Trends and Technology*, vol. 4, no. 10, pp. 4484–4489, 2013.
- P. Khobklang, K. Nokkaew, and V. Greepala,
3. "Effect of bagasse ash on water absorption and compressive strength of lateritic soil interlocking block," in *Proceedings of the International Conference on Excellence in Concrete Construction Through Innovation*, M. C. Limbachiya and H. Y. Kew, Eds., pp. 181–185, Kingston Upon Thames, London, UK, September 2008.] V. Greepala and R. Parichartpreecha,
4. "Effects of using flyash, rice husk ash and bagasse ash as replacement materials on the compressive strength and water absorption of lateritic soil-cement interlocking blocks," in *Proceedings of the 9th Australasian Masonry Conference*, pp. 583–603, Queenstown, New Zealand, February 2011.] M. Balakrishnan and V. S. Batra,
5. "Valorization of solid waste in sugar factories with possible applications in India: a review," *Journal of Environmental Management*, vol. 92, no. 11, pp. 2886–2891, 2011. N. Partha and V. Sivasubramanian,
6. "Recovery of chemicals from pressmud—a sugar industry waste," *Indian Chemical Engineer*, vol. 48, no. 3, pp. 160–163, 2006. R. L. Yadav and S. Solomon, "Potential of developing sugarcane by-product based industries in India," *Sugar Tech*, vol. 8, no. 2-3, pp. 104–111, 2006. S. R. Teixeira, A. E. De Souza, G. T. De Almeida Santos, A. F. V. Peˆna, and A. G. Miguel,
7. "Sugarcane bagasse ash as a potential quartz replacement in red ceramic," *Journal of the American Ceramic Society*, vol. 91, no. 6, pp. 1883–1887, 2008. K. Umamaheswaran, V. S. Batra, and D. V. S. Bhagavanulu,
8. "Development of biomass ash filters for high temperature applications," in *Proceedings of the International Symposium of Research Students on Materials Science and Engineering*, pp. 1–8, IIT-Madras, Chennai, India, December 2004. Sales and S. A. Lima.
9. "Use of Brazilian sugarcane bagasse ash in concrete as sand replacement," *Waste Management*, vol. 30, no. 6, pp. 1114–1122, 2010. G. Sua-iam and N. Makul,
10. "Use of increasing amounts of bagasse ash waste to produce self-compacting concrete by adding limestone powder waste," *Journal of Cleaner Production*, vol. 57, pp. 308–319, 2013. J. A. Sadeeq, J. Ochebo, A. B. Salahuddin, and S. T. Tijjani,
11. "Effect of bagasse ash on lime stabilized lateritic soil," *Jordan Journal of Civil Engineering*, vol. 9, no. 2, pp. 203–213, 2015. K. C. Onyelowe, "Cement stabilized akwete lateritic soil and the use of bagasse ash as admixture," *International Journal of Science and Engineering Investigations*, vol. 1, no. 2, pp. 16–20, 2012.